

CB MINERALS LLC
2005 Palmer Avenue, #1140
Larchmont, NY 10538
(914) 777-3330
info@cbminerals.com

Alumina Trihydrate 130

Typical Physical Properties

Median Particle Size (Microns)	19
Retained on 325 Mesh (%)	30
Retained on 200 Mesh (%)	9.4
Retained on 100 Mesh (%)	0.5
Specific Gravity	2.42
Bulk Density (lb/ft ³)	.60
Bulk Factor (gal/lb)	.0495
Free Moisture Max.	0.5
TAPPI Brightness	90
Oil Absorption	28