

CB MINERALS LLC
2005 Palmer Avenue, #1140
Larchmont, NY 10538
(914) 777-3330
info@cbminerals.com

Calcium Sulfate – White Molding Plaster

This is a high purity general purpose plaster that can be used in a wide variety of applications. The physical properties can be varies depending upon the desired end use.

Typical Properties:

Normal Consistency	74 lbs. water/100 lbs. product (34kg water/45 kg product)
Hand Mix Vicat Set, Range	25 – 50 minutes
Compressive Strength, One Hour After Set	850 - 1250 psi (5.9 – 8.6 MPa)
Compressive Strength, Dry	1700 - 2500 psi (11.7 – 17.2 MPa)
pH Reaction	Alkaline
% Expansion	.15% - 0.20%
% Passing – 50 mesh	99% - 100%
% Passing – 200 mesh	98.5% - 100%

Origin: USA