

CB MINERALS LLC

2005 Palmer Avenue, #1140

Larchmont, NY 10538

(914) 777-3330

info@cbminerals.com

SPECIALTY (acid) GRADE FLUORSPAR

Physical Form:	Dried Filter Cake
Specific Gravity:	3.18
Hardness (Mohs):	4
Melting Point:	2,450 F
Bulk Density:	100 PCF

CHEMICAL ANALYSIS (percent by weight):

	Typical	Range
Calcium Fluoride	96.0	95.0 – 97.5
Silica	1.4	0.7 – 1.8
Calcium Carbonate	1.5	1.5 – 2.5

TYPICAL PHYSICAL ANALYSIS (percent by weight, non-cumulative)

Mesh	Coarse	Regular	Fine
+20	0	0	0
-20, +40	0	1	0
-40, +100	54	15	1
-100, +200	42	26	19
-200, +325	2	20	30
-325	2	39	50